



MS APPEAL BRIEF - PATENTS
PATENT
2185-0532P

IN THE U.S. PATENT AND TRADEMARK OFFICE

In re application of	Before the Board of Appeals
HIGASHI, Kenichi et al.	Appeal No.:
Appl. No.: 09/842,248	Group: 1773
Filed: April 26, 2001	Examiner: NAKARANI, D.S.
Conf.: 7514	
For: LAMINATED FILM AND STRUCTURE COMPRISING SAME	

APPEAL BRIEF TRANSMITTAL FORM

MS APPEAL BRIEF - PATENTS

Commissioner for Patents
P.O. Box 1450
Alexandria, VA 22313-1450

December 23, 2004

Sir:

Transmitted herewith is an Appeal Brief on behalf of the Appellants in connection with the above-identified application.

- ☐ The enclosed document is being transmitted via the Certificate of Mailing provisions of 37 C.F.R. § 1.8.

A Notice of Appeal was filed on October 25, 2004.

- ☐ Applicant claims small entity status in accordance with 37 C.F.R. § 1.27

The fee has been calculated as shown below:


- ☐ Extension of time fee pursuant to 37 C.F.R. §§ 1.17 and 1.136(a) - \$0.00.
- ☒ Fee for filing an Appeal Brief - \$500.00 (large entity).
- ☒ Check(s) in the amount of \$500.00 is(are) attached.
- ☐ Please charge Deposit Account No. 02-2448 in the amount of \$0.00. A triplicate copy of this sheet is attached.

If necessary, the Commissioner is hereby authorized in this, concurrent, and future replies, to charge payment or credit any overpayment to Deposit Account No. 02-2448 for any additional fees required under 37 C.F.R. §§ 1.16 or 1.17; particularly, extension of time fees.


Respectfully submitted,

BIRCH, STEWART, KOLASCH & BIRCH, LLP

By

 #32,881

Raymond C. Stewart, #21,066


RCS/KJR:bmp
2185-0532P

P.O. Box 747
Falls Church, VA 22040-0747
(703) 205-8000

Attachment(s)



MS APPEAL BRIEF - PATENTS
PATENT
02185-0532P

IN THE U.S. PATENT AND TRADEMARK OFFICE

In re application of Before the Board of Appeals
HIGASHI, Kenichi et al.

Appl. No.:	09/842,248	Group:	1773
Filed:	April 26, 2001	Examiner:	Nakarani, D.S.
Conf.:	7514		
For:	LAMINATED FILM AND STRUCTURE COMPRISING SAME		

A P P E A L B R I E F



MS APPEAL BRIEF - PATENTS
PATENT
2185-0532P

IN THE U.S. PATENT AND TRADEMARK OFFICE

In re application of	Before the Board of Appeals
HIGASHI, Kenichi et al.	Appeal No.:
Appl. No.: 09/842,248	Group: 1773
Filed: April 26, 2001	Examiner: Nakarani, D.S.
Conf.: 7514	
For:	LAMINATED FILM AND STRUCTURE COMPRISING SAME

APPEAL BRIEF UNDER 37 CFR §41.37

Appellants submit the following Appeal Brief in connection with the Notice of Appeal filed on October 25, 2004 in connection with the above-identified application.

(i) Real Party in Interest

The real party in interest is Sumitomo Chemical Co., Ltd. as evidenced by the assignment recorded at reel #011754 and frame #0891.

(ii) Related Appeals and Interferences

There are no related appeals or interferences associated with this application.

(iii) Status of Claims

Claims 1-19 are currently pending and finally rejected as of the Final Office Action mailed April 26, 2004. The rejection of claims 1-19 is being appealed herein.

(iv) Status of Amendments

All amendments to the claims have been entered as of the Final Office Action dated April 26, 2004. There are no outstanding amendments.

(v) Summary of Claimed Subject Matter

The present invention is directed to a laminated film comprising: (i) a resin layer (A) containing an acrylic resin, and (ii) a resin layer (B) containing a resin composition, which composition comprises: (a) 10 to 98% by weight of a propylene polymer, (b) 1 to 60% by weight of an inorganic filler, and (c) 1 to 60% by weight of a thermoplastic elastomer, provided that the sum of the components (a), (b) and (c) is 100% by weight. (Claim 1; page 3, line 20 to page 4, line 5.) The present invention is also directed to a structure comprising the laminated film and a substrate containing a polyolefin resin and

the process for making the structure. (Claims 6 and 8; page 4, lines 6-21.) The present invention is also directed to car exterior parts, interior parts and household electric appliance parts composed of the claimed structure comprising the laminated film and a substrate. (Claims 9 and 10; page 4, lines 22-24.)

The claims on appeal stand and fall together.

(vi) Grounds of Rejection to be Reviewed on Appeal

Claims 1-19 stand rejected under 35 USC § 103(a) over U.S. Patent 5,725,712 to Spain et al. (hereinafter Spain '712) in view of U.S. Patent 5,829,804 to Saeki et al. (hereinafter Saeki '804).

(vii) Argument

**Rejection under 35 USC § 103(a) Over Spain '712 in view of
Saeki '804**

A. No prima facie case of obviousness

The Examiner has failed to establish a prima facie case of obviousness by failing to show that the cited references when combined teach or suggest all the elements of the present invention of claims 1-19. The Examiner also failed to establish that one of ordinary skill in the art would be motivated to combine the cited references to arrive at the present invention.

Three criteria must be met to make out a *prima facie* case of obviousness.

- 1) There must be some suggestion or motivation, either in the references themselves or in the knowledge generally available to one of ordinary skill in the art, to modify the reference or to combine reference teachings.
- 2) There must be a reasonable expectation of success.
- 3) The prior art reference (or references when combined) must teach or suggest all the claim limitations.

See MPEP §2142 and *In re Vaeck*, 20 USPQ2d 1438 (Fed. Cir. 1991). Appellants submit that the Examiner has failed to meet all three criteria to establish a *prima facie* case of obviousness.

The Examiner attempting to establish a *prima facie* case of obviousness states in the Office Action dated October 28, 2002 in paragraph 4, that Spain discloses a laminate structure comprising a carrier film such as polyester (col. 23, lines 49-50), coated with an acrylic clear coat. An acrylic colored paint is applied over the acrylic clear coat and a chlorinated polypropylene size coat is applied over the colored paint coat forming a laminate, which is laminated onto a thermoplastic polypropylene substrate. The Examiner states that the substrate

in Spain may contain filler. The Examiner states that Spain discloses similar steps as those claimed and that the article in Spain is directed to a car part or other articles. The Examiner acknowledges that Spain '712 fails to disclose a polypropylene substrate containing filler and thermoplastic elastomer.

The Examiner relying on Saeki '804 for allegedly disclosing a resin composition comprising propylene polymer 100 wt parts, ethylene-propylene copolymer rubber 46 wt parts and talc 7.7 wt parts for making car parts, such as bumpers, which can be painted.

The Examiner states that it would be *prima facie* obvious to one having ordinary skill in the art at the time the invention was made to combine the composition of Spain '712 and the resin composition and substrate taught by Saeki '804 to make the present invention, since the resin composition in Saeki '804 used as a size coat is good for adhering paint.

1. No Motivation to Combine

Appellants submit that there is no objective teaching within Spain '712 or Saeki '804 or in the general body of knowledge within the field of art that would motivate one of

ordinary skill in the art to combine the disclosure in Spain '712 with the disclosure in Saeki '804 to arrive at the present invention.

Spain '712 discloses, in Figure 4, a laminate having a carrier sheet, a clear coat, a color coat and a size coat. The color coat is made of a thermoplastic synthetic resinous coating composition containing pigment. The clear coat is a transparent or substantially transparent thermoplastic synthetic resinous coating composition. The acrylic resin component in the clear coat can be a polymethyl methacrylate or a polyethyl methacrylate resin or a mixture of the two and other comonomers. The size coat is made of chlorinated polyolefin thermoplastic. The carrier is preferably a polyester casting film. The laminate in Figure 4 in Spain '712 is transferred to a thermoformable backing sheet, which is a semirigid, self-supporting, thin, flat sheet of a synthetic resinous material.

Comparing the above elements in Spain '712 to the elements of the present invention, Appellants submit that Spain '712 fails to disclose a film having a layer containing inorganic filler, propylene polymer and thermoplastic elastomer as is described in resin layer (B) in claim 1. The deficiencies in Spain '712 are acknowledged by the Examiner in the Office Action

dated October 28, 2002. The Examiner states that Spain fails to teach polypropylene substrate containing filler and thermoplastic elastomer.

The secondary reference, Saeki '804 is relied on by the Examiner to allegedly compensate for the deficiencies in Spain '712. The Examiner alleges that Saeki '804 discloses the resin layer (B) of the present invention, which comprises propylene polymer, inorganic filler and thermoplastic elastomer. Appellants submit that Saeki '804 discloses a resin composition comprising (A) a propylene-ethylene block copolymer, (B) a propylene homopolymer, (C) a specific ethylene-propylene copolymer rubber (EPM) and/or an ethylene-propylene-diene copolymer rubber (EPDM), (D) talc and (E) a specific polyhydroxy polyolefin. This resinous layer is not identical or equivalent to resin layer (B) recited in the present claims. The composition in Saeki '804 uses component (E) polyhydroxy polyolefin to improve the paintability of a car bumper. The present invention is able to provide an excellent laminate film without layer (B) containing polyhydroxy polyolefin as a component. Appellants submit that the missing element of the present invention, resin layer (B), is not fully taught in Saeki '804.

Appellants submit that Spain '712 does not disclose any advantage to be obtained from combining the resin composition of Spain '712 with that of Saeki '804. The object of both inventions is to provide excellent paintability and durability and appearance. However, Spain '712 relates to dry paint transfer techniques and Saeki '804 relates to traditional paint techniques. The laminate in Spain '712 is prepared by dry paint transfer-laminating techniques. The resulting laminate is thermoformed into a complex three-dimensional shape and then bonded to a plastic substrate material by injection cladding techniques. This is explained in the Abstract of Spain '712. On the other hand, Saeki '804 as referenced at column 7, line 43 to column 8, line 6 relates to traditional painting. Saeki '804 discloses automobile bumpers made of a special resin composition that has an excellent paintability. Saeki '804 also discloses undercoating the primer to the surface of the bumper made from the resin composition and painting the bumper. See column 7, line 58 and column 8, line 6. Appellants point out that Saeki '804 does not suggest that the paintability of the bumper can be improved in any other way except when using component (E) in the invention of Saeki '804.

Therefore, Appellants submit that there is no motivation for one of ordinary skill in the art to combine the cited references since there is no clear advantage or improvement to be gained from the combination. There is no suggestion to use a so-called size coat from Saiki '804 on the laminate in Spain '712, particularly since the invention in Spain '712 already has a size coat and a laminate with excellent paintability, durability and appearance. Spain does not even contemplate using a resin layer containing (A) a propylene-ethylene block copolymer, (B) a propylene homopolymer, (C) a specific ethylene-propylene copolymer rubber (EPM) and/or an ethylene-propylene-diene copolymer rubber (EPDM), (D) talc and (E) a specific polyhydroxy polyolefin. Saeki '804 does not suggest an advantage to be had from using the resinous composition of Spain '712. As such, Appellants submit that there is no motivation to combine the cited references.

2. Combination Does Not Achieve the Present Invention

Applicants submit that if one of ordinary skill in the art were motivated to combine the disclosure of Saeki '804 with the disclosure of Spain '712, one would be motivated to use a resin composition that is not equivalent to the resin layer (B) of the

present invention. The composition in Saeki '804, the secondary reference, that the Examiner contends is combinable with Spain '712, comprises (A) a propylene-ethylene block copolymer, (B) a propylene homopolymer, (C) a specific ethylene-propylene copolymer rubber (EPM) and/or an ethylene-propylene-diene copolymer rubber (EPDM), (D) talc and (E) a specific polyhydroxy polyolefin. The resin layer (B) of the present invention merely contains propylene polymer, inorganic filler and thermoplastic elastomer. There is no olefinic component in layer (B). Yet, the present invention is able to achieve the excellent properties, such as paintability and durability of the paint appearance. However, in Saeki '804 component (E), the polyhydroxy polyolefin, is used for improving the coating adhesion for excellent paintability. Clearly, the resin layer (B) of the present invention and the resin composition of Saeki '804 are not equivalent.

As such, Appellants submit that even if one of ordinary skill in the art were motivated to combine the cited references, then one would be motivated to use the composition from Saeki '804 that contains components (A)-(E) listed above. Appellants submit that if it is found that there is some motivation to combine Spain '712 and Saeki '804, then the composition of

Saeki '804, which contains component (E) the polyhydroxy polyolefin would also necessarily be used in the composition; particularly, since the laminate in Spain '712 has a size coat on the paint coat and component (E) from Saiki '804 would actually improve the desired adhesion in Spain '712. Clearly, there is no motivation to use the resin composition of Saeki '804 with Spain '712 without also using component (E), particularly since the objective is to provide good adhesion for the paint laminate.

With this being the case, Appellants submit that a reasonable combination of Spain '712 and Saeki '804 does not yield the present invention. In the resin layer (B) of the present invention no polyhydroxy polyolefin (component E of Saeki '804) is present as a component. The present invention has a good adhesive property without the presence of polyolefin resin. As a result, the structure of the present invention is also able to maintain a good appearance for a long period of time. See page 20, first paragraph in the specification. The present invention also has good superior transparency and a superior surface gloss. See page 20, second paragraph.

Moreover, Appellants submit that there is no teaching of the specific layer B-substrate combination as recited in the

present invention. The dry composite paint coating in Spain '712 comprises a clear coat, which may contain an acrylic resin and a color coat, which may also contain an acrylic resin. This dry composite paint coating is transferred to a backing sheet. See figure 7 of Spain '712. Spain '712 also discloses in Figure 12 a finished article comprising a clear coat, a color coat, a size coat, a backing sheet and a substrate. The plastic substrate material 24 can also contain filler material.

Spain '712 discloses the materials for forming the backing sheet and the structure of the backing sheet at column 16, line 55 to column 17, line 39. Appellants submit that no inorganic filler is included in the backing sheet. The backing sheet in Spain '712 is made from the same or substantially the same polymeric material as the substrate base of the finished article. Spain '712 does not teach the incorporation of inorganic filler in the backing sheet.

Appellants submit that even if the polymeric material used for making the substrate contained inorganic filler in the Spain '712 invention, this still does not teach or suggest incorporating inorganic filler in the backing sheet of Saeki '804 because the inorganic filler is not a polymeric material.

As such, Appellants submit that the presently claimed resin layer (B)-substrate combination is neither disclosed nor suggested by the combination of cited references.

3. *No Suggestion to Make the Necessary Modifications*

As stated above in section 2, the combination of Spain '712 and Saiki '804 fails to disclose or suggest all of the elements of the present invention. In order to arrive at the present invention from the combination of the disclosures, one of ordinary skill in the art would have to greatly modify the disclosures of Spain '712 and Saiki '804.

One modification necessary to arrive at the present invention from the combination of Spain '712 and Saiki '804 is that the resin composition of Saiki '804 would not contain the polyhydroxy polyolefin. Yet, Saiki '804 discloses automobile bumpers made of a special resin composition that has an excellent paintability, and Saiki '804 suggests achieving this property by incorporation of component (E) polyhydroxy polyolefin. Saiki '804 does not suggest that the paintability of the bumper can be improved when component (E) is not used. Thus, to modify Saiki '804 to meet the limitations of the present invention would go against the very objective of Saiki '804. Thus, there is no motivation to make this necessary modification.

Another necessary modification would be to alter the backing sheet and substrate of Spain '712. The backing sheet disclosed in Spain '712 does not include inorganic fillers. There is no suggestion for Spain to include inorganic fillers in the backing sheet. As such, Appellants submit that there is no motivation to make this necessary modification to arrive at the present invention.

B. Obvious to Try

At best the Examiner has pointed out a combination of references that make it "obvious to try" to attain the claimed invention. "Obvious to try" is not the standard under which to reject claims under 35 USC 103. See *In re Dow Chemical Co.*, 5 USPQ2d 1521, 1532 (Fed. Cir. 1988) (rejecting the obviousness to try standard).

Appellants submit that the Examiner is using impermissible hindsight to reconstruct the instant invention. The Examiner merely relies on Appellants' own teachings to form the obviousness rejection. The Examiner has taken the instant invention and divided it into parts. The Examiner has found modified versions of each part in a separate reference. The Examiner is attempting to combine these references to arrive at the present invention. However, neither reference suggests combining the two to arrive at the instant invention. Such hindsight reconstruction is impermissible according to MPEP 2141

and In re Deminski, 796 F.2d 436, 443 230 USPQ 313, 316 (Fed. Cir. 1986).

(viii) Conclusion

For the foregoing reasons, Appellants respectfully request that the rejection finally rejecting claims 1-19 as obvious over Spain '712 in view of Saeki '804 be reversed by the honorable board of Appeals and Interferences of the United States Patent Office and that the claims be allowed to issue in a United States Patent.


Should there be any outstanding matters that need to be resolved in the present application, by either the Examiner or the honorable board, please contact Kecia Reynolds (Reg. No. 47,021) at the telephone number of the undersigned below.

If necessary, the Commissioner is hereby authorized in this, concurrent, and future replies, to charge payment or credit any

overpayment to Deposit Account No. 02-2448 for any additional fees required under 37 C.F.R. §§ 1.16 or 1.17; particularly, extension of time fees.

Respectfully submitted,

BIRCH, STEWART, KOLASCH & BIRCH, LLP

By  #32,881
Raymond C. Stewart, #21,066

RCS/KJR:bmp/jwb
2185-0532P

P.O. Box 747
Falls Church, VA 22040-0747
(703) 205-8000

Attachment(s): Claims Appendix

(ix) **Claims Appendix**

1. (Previously Presented) A laminated film comprising:

- (i) a resin layer (A) containing an acrylic resin, and
- (ii) a resin layer (B) containing a resin composition,

which composition comprises:

- (a) 10 to 98% by weight of a propylene polymer,
- (b) 1 to 60% by weight of an inorganic filler, and
- (c) 1 to 60% by weight of a thermoplastic elastomer,

provided that the sum of the components (a), (b) and (c) is 100% by weight.

2. (Original) The laminated film according to Claim 1, wherein the resin layer (A) contains a transparent layer or a colored layer.

3. (Previously Presented) The laminated film according to Claim 1, wherein the resin layer (A) contains a transparent layer and a colored layer, wherein the transparent layer is an outermost layer.

4. (Original) The laminated film according to Claim 1, wherein the thermoplastic elastomer contains an ethylene- α -olefin copolymer.

5. (Original) The laminated film according to Claim 1, wherein the inorganic filler contains talc.

6. (Original) A structure comprising:

(I) a laminated film, which comprises:

(i) a resin layer (A) containing an acrylic resin,
and

(ii) a resin layer (B) containing a resin composition,
which composition comprises:

(a) 10 to 98% by weight of a propylene polymer,
(b) 1 to 60% by weight of an inorganic filler,
and

(c) 1 to 60% by weight of a thermoplastic
elastomer,

provided that the sum of the components (a), (b) and (c) is
100% by weight; and

(II) a substrate containing a polyolefin resin, wherein the
substrate is bound to the resin layer (B) of the laminated film.

7. (Original) The structure according to Claim 6 , wherein the polyolefin resin contains a propylene polymer.

8. (Original) A process for producing a structure, which comprises the steps of

(1) thermoforming a laminated film comprising:

(i) a resin layer (A) containing an acrylic resin,
and

(ii) a resin layer (B) containing a resin composition,
which composition comprises:

(a) 10 to 98% by weight of a propylene polymer,

(b) 1 to 60% by weight of an inorganic filler, and

(c) 1 to 60% by weight of a thermoplastic
elastomer,

provided that the sum of the components (a), (b) and (c) is 100% by weight, to obtain a molded laminated film having a form adapted to the form of an injection mold of the following step (2),

(2) fixing the molded laminated film closely on an inner surface of a cavity of the injection mold so as to contact the resin layer (A) of the molded laminated film with the inner surface of the cavity, and

(3) injecting a polyolefin resin into the mold to form a substrate, whereby obtaining a structure wherein the resin layer (B) side of the laminated film is bound to the substrate.

9. (Original) Car exterior or interior parts composed of the structure according to Claim 6.

10. (Original) Household electric appliance parts composed of the structure according to Claim 6.

11. (Previously Presented) The laminated film according to Claim 1, wherein the resin layer (A) has a thickness of from 30 to 700 μ m.

12. (Previously Presented) The laminated film according to Claim 3, wherein the transparent layer has a thickness of from 10 to 300 μ m and the colored layer has a thickness of from 20 to 400 μ m.

13. (Previously Presented) The laminated film according to Claim 1, wherein the resin composition contains 20 to 70% by weight of the propylene polymer.

14. (Previously Presented) The laminated film according to Claim 1, wherein the resin composition contains 10 to 50% by weight of the inorganic filler.

15. (Previously Presented) The laminated film according to Claim 1, wherein the resin composition contains 10 to 50% by weight of the thermoplastic elastomer.

16. (Previously Presented) The process according to Claim 8, wherein the resin layer (A) has a thickness of from 30 to 700 μ m.

17. (Previously Presented) The process according to Claim 8, wherein the resin composition contains 20 to 70% by weight of the propylene polymer.

18. (Previously Presented) The process according to Claim 8, wherein the resin composition contains 10 to 50% by weight of the inorganic filler.

19. (Previously Presented) The process according to Claim 8, wherein the resin composition contains 10 to 50% by weight of the thermoplastic elastomer.